

Production Line

Disa Line

Hand Casting

Making sand mold

melting molten iron

pouring

cooling molding

sand removal and grinding

spraying vegetable oil

spraying 3 coating enamel

150-200°C baking

800°C high temperature baking

Inspect & packaging